

FLUXOFIL M42



Cored Wires
High-strength steels

Fluxofil M42 is a seamless copper coated metal cored wire with outstanding welding characteristics in the short-arc and spray-arc ranges. Almost spatter-free when welding in the spray-arc range. Good restriking, even with a cold wire tip, thus being suitable for robotic applications. Characteristic features: good side wall fusion, smooth and finely rippled welds without undercut into the base metal. Little formation of silicates on the weld surface, so that multi-pass welds can be made without inter-run cleaning. Due to the easily controllable weld pool in the short-arc range, Fluxofil M 42 is suitable for positional welding.

Classification	
AWS	A5.28: E110C-G H4
EN	12535: T 69 4 Mn2NiCrMo M 1 H5

Approvals	Grades
DB	
TÜV	
UDT	

Analysis of all-weld metal (Typical values in %)

C	Mn	Si	P	S	Cr	Ni	Mo	Nb	V	N	Cu
0.05	1.60	0.50	-	-	0.45	1.90	0.40	-	-	-	-

All-weld metal Mechanical Properties

Heat Treatment	Yield Strength N/mm ²	Tensile Strength N/mm ²	Elongation A5 (%)	Impact Energy ISO - V (J) - 40 °C	Hardness
PWHT 580 °C x 2 h	≥ 690	760-850	≥ 15	≥ 47	-
As Welded	≥ 690	760-850	≥ 15	≥ 47	-

Gas test: Acc. To EN 439: M21

Shielding Gas: Acc. To EN 439: M21

Materials

S620, S690, HY 100

Storage

Keep dry and avoid condensation

Current condition and welding position

DC+				
PA	PB	PC	PF	PE

Packaging data: K300 kg, 16

Diameters	1.2mm				
-----------	-------	--	--	--	--

Diam.	16kg Spool
1.2mm	OERFFM4212

TALARC Pty Ltd
10-16 Syme St
Brunswick, Vic 3056
Ph. +61 3 9388 0588 Fax: +61 3 9388 0710
W: www.talarc.com E: sales@talarc.com