

TALARC B2

CLASSIFICATION

AWS SPECIFICATIONS	EN SPECIFICATIONS
AWS A 5.28: ER80S-B2	EN ISO 21952-B: G 1CM

ALLOY TYPE

1.25Cr-0.5Mo content to be used for the welding of creep resistant steel.

APPLICATIONS

Low alloy copper-coated solid wire with 1.25% Cr and 0.5% Mo content to be used for the welding of creep resistant steel. Chemical composition of wire conforming to AWS specification. It is used in chemical industry and in the ammonia synthesis process, for heat exchangers, boilers, piping and pressure vessels for temperature service up to about 550°C. It will also find applications in the petro-chemical industries, suitable for facing on casting and for casting repairs. To be used under the shield of Ar+O₂.

TYPICAL CHEMICAL COMPOSITION OF WIRE

C %	Mn %	Si %	S %	P %	Cr %	Ni %	Mo %	Cu %
0.08	0.60	0.60	0.010	0.010	1.30	-	0.50	0.12

TYPICAL MECHANICAL PROPERTIES

GAS		Yield strength	Tensile strength	Elongation on % 5d	Impact energy (Charpy V)				
		Rs	Rm	A 5d	+ 20°C	0°C	-20°C	-40°C	-60°C
		(MPa)	(MPa)	%	(Joule)	(Joule)	(Joule)	(Joule)	(Joule)
MIX	after PWHT	460	570	23	150	-	-	-	-

WELDING GUIDELINES

Preheat and interpass temperature 150°C. PWHT at 620°C for an hour.

TECHNICAL INFORMATION

Gas: Mix Ar- O₂ (EN ISO 14175)

Welding positions: all positions



WELDING PARAMETERS

Current	DC + Reverse polarity				
Diameter (mm)	0.8	1.0	1.2	1.6	
Volts (V)	16 ÷ 28	17 ÷ 32	18 ÷ 34	19 ÷ 38	
Intensity (A)	60 ÷ 200	80 ÷ 260	100 ÷ 360	130 ÷ 450	

Diam.	5kg Spool	15kg Spool
0.9mm	INMB20905	INMB20915
1.2mm		INMB21215

TALARC Pty Ltd
10-16 Syme St
Brunswick, Vic 3056
Ph. +61 3 9388 0588 Fax: +61 3 9388 0710
W: www.talarc.com E: sales@talarc.com