

# TALARC R60

## CLASSIFICATION

AWS SPECIFICATIONS	EN SPECIFICATIONS
AWS A 5.2: R60	EN 12536: O II

## ALLOY TYPE

Copper-coated steel rod for oxy-acetylene welding of carbon and C – Mn steels of medium mechanical properties.

## APPLICATIONS

Special copper-coated steel rod designed for oxy-acetylene (autogenous) welding of carbon or carbon-manganese steels of medium mechanical properties. Suitable as well for welding construction steels.

## TYPICAL CHEMICAL COMPOSITION OF WIRE

C %	Mn %	Si %	S %	P %	Cu %	Ni %	Cr %	Mo %
0.10	1.00	0.20	0.012	0.012	0.15	-	-	-

## TYPICAL MECHANICAL PROPERTIES

GAS		Yield strength	Tensile strength	Elongation on % 5d	Impact energy (Charpy V)			
		Rs	Rm	A 5d	+ 20°C	-20	-30°C	-40°C
		(MPa)	(MPa)	%	(Joule)	(Joule)	(Joule)	(Joule)
/	as welded	-	520	-	-	-	-	-

## WELDING GUIDELINES

Preheat and PWHT are not required.

## TECHNICAL INFORMATION

Gas: Oxy-acetylene  
Welding position: all positions



## PACKAGING DATA

Diameter (mm)	1.6	2.4
Length (mm)	1000	1000
Carton	5 Kg	5 Kg

Diam.	5 kg Tube
1.6mm	INTR6016
2.4mm	INTR6024

TALARC Pty Ltd  
10-16 Syme St  
Brunswick, Vic 3056  
Ph. +61 3 9388 0588 Fax: +61 3 9388 0710  
W: [www.talarc.com](http://www.talarc.com) E: [sales@talarc.com](mailto:sales@talarc.com)