



## BÖHLER Ti 52 T-FD (HP)

Flux cored wire, seamless, unalloyed, rutile type

### Classifications

EN ISO 17632-A	EN ISO 17632-B	AWS A5.36	AWS A5.36M
T46 5 P M21 1 H5	T554T1-1M21A-H5	E71T1-M21AP6-CS2-H4	E491T1-M21AP5-CS2-H4
T42 2 P C1 1 H5	T492T1-1C1A-H5	E71T1-C1A0-CS2-H4	E491T1-C1A2-CS2-H4

### Characteristics and typical fields of application

High performance seamless rutile flux cored wire for single or multipass welding of Carbon, Carbon-Manganese steels and similar including fine grain steels with Argon-CO<sub>2</sub> shielding gas or pure CO<sub>2</sub>. Main features: excellent weldability in all positions, excellent bead appearance, very low spatter losses, fast freezing slag with an easy removal. The good mechanical properties of this wire make it especially suitable for hardest applications in off-shore and ship building industry even at low temperatures. This product can be used in sour gas applications. (HIC tested acc. to NACE TM-0284). Test values for SSC are available upon request.

### Base materials

S235JR-S355JR, S235JO-S355JO, S450JO, S235J2-S355J2, S275N-S460N, S275M-S460M, P235GH-P355GH, P275NL1-P460NL1, P215NL, P265NL, P355N, P285NH-P460NH, P195TR1-P265TR1, P195TR2-P265TR2, P195GH-P265GH, L245NB-L415NB, L450QB, L245MB-L450MB, GE200-GE240

Ship building steels: A, B, D, E, A 32-E 36

ASTM A 106 Gr. A, B, C; A 181 Gr. 60, 70; A 283 Gr. A, C; A 285 Gr. A, B, C; A 350 Gr. LF1; A 414 Gr. A, B, C, D, E, F, G; A 501 Gr. B; A 513 Gr. 1018; A 516 Gr. 55, 60, 65, 70; A 573 Gr. 58, 65, 70; A 588 Gr. A, B; A 633 Gr. C, E; A 662 Gr. B; A 711 Gr. 1013; A 841 Gr. A;

API 5 L Gr. B, X42, X52, X56, X60, X65

### Typical analysis of all-weld metal (wt.-%)

	Gas	C	Si	Mn	Ni
wt-%	M21	0.06	0.45	1.30	0.35
wt-%	C1	0.05	0.35	1.00	0.30

### Mechanical properties of all-weld metal

Condition	Yield strength R <sub>e</sub>	Tensile strength R <sub>m</sub>	Elongation A (L <sub>0</sub> =5d <sub>0</sub> )	Impact work ISO-V KV J		
				-20°C	-40°C	-50°C
u	<b>500</b> (≥460)	<b>590</b> (550–660)	<b>28</b> (≥20)	<b>110</b>	<b>90</b> (≥47)	<b>80</b> (≥47)
u1	<b>450</b> (≥420)	<b>550</b> (500–640)	<b>24</b> (≥20)	<b>100</b> (≥47)		
	MPa	MPa	%	-	-50°F	-60°F
s1	<b>510</b> (≥460)	<b>590</b> (550–660)	<b>26</b> (≥20)	-	<b>80</b> (≥27)	<b>60</b> (≥27)
s2	<b>500</b> (≥460)	<b>580</b> (550–660)	<b>22</b> (≥20)	-	<b>62</b>	<b>60</b>

u untreated, as welded – shielding gas M21

u1 untreated, as welded – shielding gas C1

s1 stress released, 620 °C x 1 hr - shielding gas M21

s2 stress released, 620 °C x 5 hr - shielding gas M21

Diam.	15kg spool
1.2mm	BOTI52TFDHP12

TALARC Pty Ltd  
10-16 Syme St  
Brunswick, Vic 3056  
Ph. +61 3 9388 0588 Fax: +61 3 9388 0710  
W: [www.talarc.com.au](http://www.talarc.com.au) E: [sales@talarc.com](mailto:sales@talarc.com)