

Datasheet RM02

Cast Iron Filler Metal

NI-ROD® 99 Filler Metal

NI-ROD 99 Filler Metal is used for gas-metal-arc, gas-tungsten-arc and submerged-arc welding of ductile, malleable, and gray cast irons. It is a solid nickel alloy wire designed for making easily machined welds by automatic and semi-automatic processes. In highly diluted, single-layer deposits, pure nickel weld metal has better machinability than other welding products for cast irons.

Disimilar-welding applications include gas-metal-arc welding of cast irons to low-alloy and carbon steels.

Specifications

AWS A5.15 ERNi-CI (UNS N02215)

ASME II, Part C, SFA-5.15, ERNi-CI(UNS NO2215)

*BS 2901 NA46

*(EN) ISO 1071 S CI 4003 (S C Ni-CI)

*Supply to these specifications available upon request

For manufacture to ASME III (NCA3800, NB2400), and other specifications please refer your inquiry to the Technical Department prior to order placement.

Approvals

Please confirm details of current scope of approvals with the Technical Department prior to order placement.

Limiting	Ni+Co 99.0 min.	Cu 0.25 max.
Chemical	Fe 0.40 max.	C 0.15 max.
Composition	Mn 0.35 max.	S 0.01 max.
•	Si 0.35 max.	Others 1.00 max.
Typical	Tensile Strength, psi	71,000
Mechanical	MPa	490
Properties	Elongation, (4d) %	12

Filler metals available on spool and in cut straight lengths in a variety of sizes selected from the following diameters:

Availe	Available Product Forms							
mm	0.8	0.9	1.0	1.14	1.2	1.6	2.4	3.2
	0.030	0.035	0.040	0.045	0.047	0.062	0.093	0.125

Diam.	13.62 kg Spool				
0.9mm	SMMNIROD9909				
1.2mm	SMMNIROD9912				

TALARC Pty Ltd 10-16 Syme St Brunswick, Vic 3056 388 0588 Fay: +61 3 9388 07

Ph. +61 3 9388 0588 Fax: +61 3 9388 0710 W: www.talarc.com E: sales@talarc.com