


PREMIARC™ TG-X308L

Flux cored filler rod

- Features:**
- Applicable for 304 and 304L type steels
 - Suitable for root pass in one-side welding without back shielding
 - In order to avoid defects, TG-X filler rod must be moved quickly at short pitch, unlike TIG filler rod

Classification: AWS A5.22 R308LT1-5
Shielding gas: Ar
Identification color: Red
Polarity: DCEN

Welding Positions:



Packaging data

			Tube	
φ mm	kg	Length mm	g/piece	Volume mm
2.2	5	1,000	26	42W, 35H, 1015L

Composition (all-weld metal mass %)

	Typical	Guaranty ^a
C	0.02	0.03
Si	0.7	1.2
Mn	1.4	0.5-2.5
P	0.02	0.04
S	<0.01	0.03
Ni	10.3	9.0-11.0
Cr	19.6	18.0-21.0
Mo	0.02	0.75
Cu	0.04	0.75
Bi	>0.002	-

Note: ^aSingle values are maximum.

Welding parameters (A)

thickness mm	3-5	6-9	Over 10
current A	80-90	90-105	90-110

All-weld mechanical properties

	Typical	Guaranty
0.2%YS (MPa)	450	-
TS (MPa)	620	518min.
EI on 4d (%)	47	30min.
IV -196°C (J)	60	-

Diam.	Part No.
2.2mm	KOBE TGX308L

TALARC Pty Ltd
 10-16 Syme St
 Brunswick, Vic 3056
 Ph. +61 3 9388 0588 Fax: +61 3 9388 0710
 W: www.talarc.com.au E: sales@talarc.com