


PREMIARC™ TG-X316L

Flux cored filler rod

- Features:**
- Applicable for 316 and 316L type steels
 - Suitable for root pass in one-side TIG welding without back shielding
 - In order to avoid defects, TG-X filler rod must be moved quickly at short pitch, unlike TIG filler rod

Classification: AWS A5.22 R316LT1-5
Shielding gas: Ar
Identification color: Green
Polarity: DCEN



Packaging data

			Tube	
φ mm	kg	Length mm	g/piece	Volume mm
2.2	5	1,000	26	42W, 35H, 1015L

Composition (all-weld metal mass %)

	Typical	Guaranty ^a
C	0.02	0.03
Si	0.7	1.2
Mn	1.4	0.5-2.5
P	0.02	0.04
S	<0.01	0.03
Ni	12.0	11.0-14.0
Cr	18.4	17.0-20.0
Mo	2.2	2.0-3.0
Cu	0.05	0.75
Bi	>0.002	-

Note: ^aSingle values are maximum.

Welding parameters (A)

thickness mm	3-5	6-9	Over 10
current A	80-90	90-105	90-110

All-weld mechanical properties

	Typical	Guaranty
0.2%YS (MPa)	440	-
TS (MPa)	600	483min.
El on 4d (%)	38	30min.
IV 0°C (J)	110	-

Approvals / [Click here for certificates](#)

NK	MG
----	----

Diam.	Part No.
2.2mm	KOBE TGX316L

TALARC Pty Ltd
 10-16 Syme St
 Brunswick, Vic 3056
 Ph. +61 3 9388 0588 Fax: +61 3 9388 0710
 W: www.talarc.com.au E: sales@talarc.com